MAXXON®
COMMERCIAL

Level EZ™ + Fibers



THE FIBER-REINFORCED SELF-LEVELER.

Maxxon® Commercial Level EZ™ + Fibers is a high-performance, fiber-reinforced self-leveling underlayment that delivers exceptional toughness without the need for reinforcement mesh. Engineered for superior crack resistance, its high-flow formula ensures smooth, flat surfaces over wood, gypsum, or concrete, making it an ideal choice for fast-track commercial and multifamily projects.

- A highly flowable, fiber reinforced self-leveling underlayment
- Designed to eliminate the need for reinforcement fabric
- Engineered to minimize cracking
- Installation from featheredge up to 2"
- Foot traffic in 2–4 hours, typically
- Trade traffic in 24 hours
- Suitable for virtually all floor coverings
- Floor installation in as little as 16 hours

BENEATH IT ALL, MAXXON DELIVERS.™

WHERE TO USE

Application
Multifamily wood frame, light commercial wood frame, commercial, concrete construction and renovation.

Subfloor
Interior gypsum, concrete, wood.

5,000–7,000 PSI

MAXXON® COMMERCIAL
Level EZ™ + Fibers

FIBER REINFORCEMENT FOR ADDED DURABILITY

Enhanced with fibers, Maxxon Commercial Level EZ + Fibers minimizes the risk of cracking, even in challenging commercial applications. Choose a high-performance underlayment that saves time and money by allowing you to simply clean, prime, and pour — no shotblasting required.

With its smooth, dimensionally stable formula, this underlayment can be applied from featheredge up to 2" depths and is walkable within 2–4 hours, ensuring you meet your timelines. Maxxon Commercial Level EZ + Fibers works seamlessly with carpet, ceramic tiles, LVT, and more, resulting in a durable, flat surface free from buckling, heaving, or curling.

PRODUCT INFORMATION

Compressive Strength (Modified ASTM C109)	24 hrs.: 2,000 psi (13.8 MPa) 7 days: 2,700 psi (18.6 MPa) 28 days: 5,000 to 7,000 psi (34.5 – 48.3 MPa)
Installation Depths	Featheredge to 2" (0–51 mm) For deeper pours, contact Maxxon
Flexural Strength (ASTM C348)	1,500 psi (10.3 MPa) when dry
Dry Density	115–125 lbs/ft^3 (1,842–2,002 kg/m^3)
Working Time	15–20 min.
Coverage (per 50 lb bag)	Approximately 24 ft^2 at 1/4"*
Fire Performance (ASTM E84)	Flame spread: 0 Fuel contribution: 0 Smoke development: 0

* Depending on water demand used and slab condition.



INSTALLATION & LIMITATIONS

See technical data sheet available at Maxxon.com for limitations and complete installation instructions.

PACKAGING

50 lbs (22.7 kg)

FIRE RATINGS

Underwriters Laboratory International UL ER #8477-01. See technical data sheet for complete UL and fire assembly information.

GREENGUARD GOLD — PRODUCT CERTIFIED FOR LOW CHEMICAL EMISSIONS UL.COM/GG UL 2818

GREENGUARD — PRODUCT CERTIFIED FOR LOW CHEMICAL EMISSIONS UL.COM/GG UL 2818

UL LISTED

Maxxon Corporation
920 Hamel Road PO Box 253
Hamel, Minnesota 55340
800-238-8461
maxxon.com
info@maxxon.com

@Maxxon.Corporation
maxxon-corporation

©2025 Maxxon Corporation. All Rights Reserved. Maxxon Commercial Level EZ and associated logos are registered trademarks of Maxxon Corporation, Hamel, MN, USA. SS021-05/26